Adsorption-induced conversion of the carbon nanotube field effect transistor from ambipolar to unipolar behavior

Donghun Kang, Noejung Park, Jaewoong Hyun, Eunju Bae, Juhye Ko, Jujin Kim, and Wanjun Park

Citation: [Applied Physics Letters](#) **86**, 093105 (2005); doi: 10.1063/1.1869548

View online: <http://dx.doi.org/10.1063/1.1869548>

View Table of Contents: <http://scitation.aip.org/content/aip/journal/apl/86/9?ver=pdfcov>

Published by the [AIP Publishing](#)

Articles you may be interested in

[Hysteretic transfer characteristics of double-walled and single-walled carbon nanotube field-effect transistors](#)
Appl. Phys. Lett. **91**, 143118 (2007); 10.1063/1.2789789

[Room-temperature single charge sensitivity in carbon nanotube field-effect transistors](#)
Appl. Phys. Lett. **89**, 243502 (2006); 10.1063/1.2399942

[Ab initio study of the effect of water adsorption on the carbon nanotube field-effect transistor](#)
Appl. Phys. Lett. **89**, 243110 (2006); 10.1063/1.2397543

[Prospect of cobalt-mix-tetraethoxysilane method on localized lateral growth of carbon nanotubes for both p - and n -type field effect transistors](#)
J. Vac. Sci. Technol. B **24**, 2282 (2006); 10.1116/1.2345207

[Self-assembled carbon-nanotube-based field-effect transistors](#)
Appl. Phys. Lett. **85**, 5025 (2004); 10.1063/1.1823017

A promotional banner for the 2014 Special Topics in Applied Physics Letters (APL) Materials. The banner has an orange background with a white border. At the top, the text '2014 Special Topics' is written in a large, white, sans-serif font. Below this, there are five circular icons, each containing a different material structure and a label: 'PEROVSKITES' (red and black geometric structure), '2D MATERIALS' (blue and red hexagonal lattice), 'MESOPOROUS MATERIALS' (green and yellow porous structure), 'BIOMATERIALS/ BIOELECTRONICS' (yellow and green biological structure), and 'METAL-ORGANIC FRAMEWORK MATERIALS' (brown and yellow porous structure). At the bottom left, the 'AIP | APL Materials' logo is displayed. At the bottom right, a red banner with white text says 'Submit Today!'.

Adsorption-induced conversion of the carbon nanotube field effect transistor from ambipolar to unipolar behavior

Donghun Kang, Noejung Park, Jaewoong Hyun, Eunju Bae, Juhye Ko, Jujin Kim,^{a)} and Wanjun Park^{b)}

Materials and Devices Lab., CSE Lab., Samsung Advanced Institute of Technology, Mt.14-1, Neongseo-Ri, Giheung-Eup, Yongin City, Gyeonggi-Do 449-712, Korea

(Received 26 July 2004; accepted 18 January 2005; published online 23 February 2005)

We investigate ambipolar to unipolar transition by the effect of ambient air on the carbon nanotube field-effect transistor. A unipolar transport property of the double-walled nanotube field-effect transistor and its conversion from ambipolar behavior are observed. We suggest that adsorptions of oxygen molecules, whose lowest-unoccupied-molecular-orbital state is around the midgap of the carbon nanotube, could suppress the electron channel formation and, consequently, result in the unipolar transport behavior. © 2005 American Institute of Physics. [DOI: 10.1063/1.1869548]

Since the discovery of carbon nanotubes (CNTs),¹ their various aspects have been explored in different fields of science and technology. In particular, the unique one-dimensional geometry and the excellent transport property have made CNTs the most promising building blocks for the next-generation electronic devices.^{2,3} The most important application in electronics is the CNT field effect transistor (FET).⁴ However ambipolar behavior in CNT-FET (Ref. 5) limits in the development of nanotube-based integrated circuit application by unexpected leakage current before the turn-on bias.

In this work, we show a unipolar transport property of the double-walled nanotube (DWNT) FET and its conversion from ambipolar behavior. We choose DWNT-FET to maximize ambipolar behavior⁶ since it is mainly ascribed to the smaller band gap arising from the large diameter of outer shell. Purified DWNTs were suspended in a solvent and spin coated on the SiO₂ grown on heavily doped *p*-type Si substrate. Scanning probe microscopy locates individually separated nanotubes on the substrate. After generating patterns for metal contact by electron-beam lithography, metal electrodes with 100 nm Pd were defined by the lift-off process. Typical system resistances without gate bias were in the range of several hundreds of kΩ to MΩ. Electrical measurement was carried out in a probe station chamber equipped with a pumping unit, which can pump down the chamber to 10⁻⁶ Torr.

In Fig. 1, we present the current-voltage (I_{ds} - V_g) curves of the DWNT-FET measured with various source and drain voltages (V_{ds}) under the influence of ambient air. A typical *p*-channel behavior is observed in our DWNT-FET. It could be described as a device operating in *p*-channel depletion mode, whose turn-off voltages are about $V_g=4$ V. With careful examination, it is observed that there are small bumps in the I_{ds} - V_g curves at about 3 V above the turn-off voltage. In the latter part, we discuss that the observed small bumps and traces of current in the positive side of gate voltage could indicate the suppression of electron channel formation.

We now turn to investigate the transfer characteristics of CNT-FET in different vacuum conditions. In Fig. 2, we plot the I_{ds} - V_g curves of DWNT-FET at several intermediate pumping stages from ambient air to vacuum of 3×10^{-6} Torr. The *n*-channel starts to emerge and the FET gradually shows an ambipolar behavior as it passes through the several pumping stages. After 72 h of pumping, we have a complete conversion of transport property of DWNT-FET from unipolar to ambipolar. In fact, the overall conversion process can be reversible and can reproduce the patterns that are shown in Fig. 2.

Heinze *et al.*⁷ discussed that the work function variation in the electrode leads to an asymmetric change in the I_{ds} - V_g curve, inducing less current for one polarity of gate bias and more current for the opposite polarity under the influence of ambient air. Such a change has largely attributed to the oxygen effect. Derycke *et al.*⁸ reported that the exposure to air or oxygen induced an increase in the work function of the gold electrode, which resulted in ambipolar behavior. Indeed, we observe a similar effect of ambient air on our DWNT-FET which shows an increase in the *p*-channel transport as well as a decrease in the *n*-channel conduction, leading to asymmetric I_{ds} - V_g patterns. It is noticed that the I_{ds} - V_g curve for our DWNT-FET shows a symmetriclike transport behavior under the high-vacuum condition, but this symmetry goes away as the system is slowly exposed to air.

Although a part of our results is consistent with previous works,^{7,8} the unipolar behavior of DWNT-FET in ambient air, as shown in Fig. 1, needs more comprehensible arguments. It is reasonable to assume that there are significant molecular adsorptions on the wall of CNT as well as on the surface of metal electrode. Provided that the lowest unoccupied molecular orbital (LUMO) levels of the adsorbators sit somewhere in the gap of the CNT, electrons would occupy the molecular levels under a positive gate voltage, as shown in Figs. 3(a) and 3(b). As a result, the electrostatic potential generated by the negatively charged adsorbators screens the gate field and, consequently, suppresses the electron channel formation. The nanotube bands in the channel region would resist a downshift because of the presence of charged adsorbators. Two upward arrows in Fig. 3(b) describe the effect of such an electrostatic potential generated by the charged adsorbators. On the other hand, conduction bands of a clean

^{a)}Also at: Department of Physics, Chonbuk National University, Jeonju 561-756, Korea.

^{b)}Author to whom correspondence should be addressed; electronic mail: wanjun@samsung.com

FIG. 1. (Color) (a) The upper panel shows I_{ds} - V_g curves of the DWNT-FET under the influence of ambient air condition with various source-drain voltages. A schematic drawing of the device is given in inset. (b) Scanning electron microscopy figure of the DWNT-FET and high-resolution transmission electron microscopy figure of DWNT used for this work.

nanotube shift down allowing electron current under such a positive gate voltage, as shown in Fig. 3(c). It is noticed that the V_g difference between the onset voltage of p -channel and the bumps in Figs. 1 and 2 is about 3 V, which is similar to the off-state range of the DWNT-FET under a vacuum. Thus, based on this theory, the small bumps in the I_{ds} - V_g curves and subsequent small traces of the current tailing in the positive side of V_g would be precursors of n channels in the otherwise ambipolar DWNT-FET.

We performed *ab initio* density-functional (DFT) calculations using the basis of plane-wave set with the cutoff energy of 500 eV.^{9,10} The ultrasoft pseudopotentials are implemented for the ionic potentials,¹¹ and the generalized gradient approximation (GGA) is used for the exchange-correlation potential.¹² Since it is well known that the influences of O_2 and H_2O are significant on the device performance of CNT-FET,^{7,8,13} it is necessary to investigate the effect of these molecules on the CNT. The (10,0) CNT,

FIG. 2. (Color) Transfer characteristics of DWNT-FET under ambient air, vacuum of 3×10^{-6} Torr, and at intermediate pumping stages.

FIG. 3. (Color) Schematic band structure of the carbon nanotube (blue) and the LUMO level of the adsorbators (red), with respect to the Fermi level.

whose band gap is found to be 0.7 eV, is exploited as an example for a typical semiconducting CNT. Despite the fact that commonly synthesized nanotubes may have a larger diameter than the (10,0) nanotube, the results, which will be discussed in this paragraph, can be applied for such large diameter semiconducting nanotubes. Twice the minimal unit cell of the zigzag nanotube (≈ 8.49 Å) is used for the unit cell along the axial direction of the CNT. Along the perpendicular direction to the axis, the nanotube is separated from its replica with a large vacuum region of about 10 Å. As shown in Fig. 4, the fully relaxed O_2 position is located in between two C-C bonds with a binding energy of 0.013 eV, which is in an overall agreement with the previous works.^{14,15} The dispersion forces are not dealt within the DFT calculations. However, a proper consideration of dispersion forces would increase the binding energy about 0.1 eV over that of the GGA value.¹⁴ In fact, we observe that the LUMO level of oxygen lies somewhere in the gap of the CNT. Since the oxygen adsorption on the surface of nanotube is a weak physisorption with negligible charge transfer,^{15,16} two half-filled $pp\pi^*$ states should be around the Fermi level of the CNT. In other words, there should be unoccupied molecular levels at or just above the Fermi level, irrespective of the diameter of the semiconducting CNT.

The effect of oxygen adsorption on CNT has been controversial. An earlier study suggested that the binding energy of O_2 on CNT wall is strong, and thus the substantial charge transfer results in the hole doping of the CNT.¹⁷ Subsequent studies have declined the possibility of the O_2 -induced hole doping.¹⁴⁻¹⁶ However, we have found that the LUMO level of O_2 adsorbators could provide the charge trapping centers,

FIG. 4. (Color) Adsorption geometry of oxygen molecule on the wall of the (10,0) nanotube and *ab initio* band structure of the oxygen adsorbed nanotube system. Arrows in (b) indicate oxygen molecular states.

irrespective of the possibility of a practical hole doping by the oxygen adsorption. These charge trapping centers could screen the electric field from the positively biased gate, resulting in the suppression of electron channel formation.

We performed the same calculation for the water-adsorbed CNT, adopting the adsorption geometry discussed in literature.¹⁸ It is found that the LUMO level of H₂O is about 4 eV above the Fermi level of the CNT. Thus, it is believed that the effect of water vapor on the aforementioned suppression of the *n*-channel formation is insignificant.¹⁹

In summary, we observed a unipolar behavior of DWNT-FET under ambient air. We suggest that electrons trapped by the adsorbators, whose LUMO level is in the band gap of the CNT, suppress the *n*-channel formation on the positive gate voltage, leading to a unipolar transfer characteristic. Through *ab initio* density-functional calculations, we concluded that the oxygen molecule could be the most probable candidate for such an adsorbator, which induces the conversion of DWNT-FET into a unipolar behavior.

The authors thank J. R. Kim and J. J. Kim at Chonbuk National University for their cooperation. This research project was supported by the Terra-level Nano Devices, Korea National Research Program.

¹S. Iijima, *Nature (London)* **354**, 56 (1991).

²A. Javey, H. Kim, M. Brink, Q. Wang, A. Ural, J. Guo, P. McIntyre, P. Mceuen, M. Lundsrtrom, and H. Dai, *Nat. Mater.* **1**, 241 (2002).

- ³S. Frank, P. Poncharal, Z. Wang, and W. Heer, *Science* **280**, 1744 (1998).
⁴R. Martel, T. Schmidt, H. R. Shea, T. Hertel, and P. Avouris, *Appl. Phys. Lett.* **73**, 2447 (1998).
⁵P. G. Collins, M. S. Arnold, and P. Avouris, *Science* **292**, 706 (2001); T. Shimada, T. Okazaki, R. Taniguchi, T. Sugai, H. Shinohara, K. Suenaga, Y. Ohno, S. Mizuno, S. Kishimoto, and T. Mizutani, *Appl. Phys. Lett.* **81**, 4067 (2002).
⁶T. Shimada, T. Sugai, Y. Ohno, S. Kishimoto, T. Mizutani, H. Yoshida, T. Okazaki, and H. Shinohara, *Appl. Phys. Lett.* **84**, 2412 (2004).
⁷S. Heinze, J. Tersoff, R. Martel, V. Derycke, J. Appenzeller, and P. Avouris, *Phys. Rev. Lett.* **89**, 106801 (2002).
⁸V. Derycke, R. Martel, J. Appenzeller, and P. Avouris, *Appl. Phys. Lett.* **80**, 2773 (2002).
⁹P. Hohenberg and W. Kohn, *Phys. Rev.* **136**, B864 (1964); W. Kohn and L. J. Sham, *Phys. Rev.* **140**, A1133 (1965).
¹⁰J. Ihm, A. Zunger, and M. L. Cohen, *J. Phys. C* **12**, 4409 (1979).
¹¹D. Vanderbilt, *Phys. Rev. B* **41**, 7892 (1990).
¹²J. P. Perdew, K. Burke, and M. Ernzerhof, *Phys. Rev. Lett.* **77**, 3865 (1996).
¹³W. Kim, A. Javey, O. Vermesh, Q. Wang, Y. Li, and H. Dai, *Nano Lett.* **3**, 193 (2003).
¹⁴S. Dag, O. Gulsere, T. Yildirim, and S. Ciraci, *Phys. Rev. B* **67**, 165424 (2003).
¹⁵P. Giannozzi, R. Car, and G. Scoles, *J. Chem. Phys.* **118**, 1003 (2003).
¹⁶H. Ulbricht, G. Moos, and T. Hertel, *Phys. Rev. B* **66**, 075404 (2002).
¹⁷S.-H. Jhi, S. G. Louie, and M. L. Cohen, *Phys. Rev. Lett.* **85**, 1710 (2000).
¹⁸R. Pati, Y. Zhang, and S. K. Nayak, *Appl. Phys. Lett.* **81**, 2638 (2002).
¹⁹Because the highest occupied molecular level (HOMO)-LUMO gap in the DFT is not so rigorous, we performed TDDFT calculations for H₂O using Gaussian package [Gaussian 03, Revision B.01, Gaussian, Inc., Pittsburgh, PA, 2003]. The HOMO-LUMO gap of H₂O is found to be 6.4 and 7.5 eV in DFT and TDDFT, respectively. Thus, the DFT artifact would not affect our model discussed here.